NuTech
Paint for a perfect finish

Quick Reference Roof Coating Guide

Product	1st Coat	Compatible with	Recoat @ 25°C	External	Uses	Additional	Application Rate per coat	Tip Size
NuPrime	No Dilution	All roof top coats	1-2 hours	Yes	Powdery oxidised roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	517-521
SupaPrime	No Dilution	All roof top coats	1-2 hours	Yes	Powdery oxidised roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	519-521
Master Sealer	No Dilution	All roof top coats	1-2 hours	Yes	Stable cement roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	519-521
Nubond	No Dilution	All roof top coats	2-4 hours	Yes	Rough, porous roof tiles and gloss enamel	Milky dries clear	1 coat @4sq.m/litre	519-521
Flexible Membrane (Barrier Coat)	No Dilution	All roof top coats	2-4 hours Not same day in cool/wet conditions	Yes	Unstable previously painted surfaces	Can be tinted to most colours	1 coat @4sq.m/litre	523-525
GP Primer	No Dilution	All roof top coats	2-4 hours Not same day in cool/wet conditions	Yes	Very rough cement roof tiles	Light Grey colour	1 coat @4sq.m/litre	523-525
Metal Primer	No Dilution	All roof top coats	2-4 hours Not same day in cool/wet conditions	Yes	Metal sheet roofing	Light Grey colour	1 coat @ 5-6sq.m/litre	523-525
Elite Terracotta Primer	No Dilution	All roof top coats	1-2 hours	Yes	Raw uncoated, Glazed & Vitrified Terracotta Tiles	Milky White	1 coat @5-12sq.m/litre Substrate dependent	519-521
Asbestos Sealer	No Dilution	All roof top coats	1-2 hours	Yes	Asbestos sheeting	Opaque White	1 coat @4sq.m/litre	519-521
NuFlex **TileFlex** **NXT Cool Zone** *(Gloss & Low Sheen)* **FlexiShield** *(Low Sheen & Matt)*	No Dilution No Dilution No Dilution No Dilution	All roof Primers & Sealers	4 hours 4 hours 4 hours 4 hours	Yes Yes Yes Yes	Trade Quality Premium Quality Ultra Premium Heat Reflective Mainly for Metal Surfaces	**10** year warranty **12** year warranty **15** year warranty **10** year warranty	2 coats @4sq.m/litre 2 coats @4sq.m/litre 2 coats @4sq.m/litre 2 coats @5sq.m/litre	519-521 519-523 519-523 519-523
Aqua Stop Silicon Sealer	No Dilution	Silicon in water	1 hour	Yes	Most porous surfaces	Do Not allow to pool on surface	2 coats @1-3sq.m/litre depending on substrate	515-519

* This is a quick reference guide only
** Primers and Sealers must be top coated
*** For complete information on all products refer to Nutech Product Data Sheets, Application Guidelines and Material Safety Data Sheet